



CFX DELUXE CLEAR BASE

Soft Hand High, Pigment Loading Paste

Technical Data Sheet

REV. 20240313

Key Features

A High Solids, PVC, Phthalate and Formaldehyde free aqueous ink system optimized for printing on automatic and manual equipment.

Formulated as a high productivity ink system with excellent open-time and an extremely soft hand Deluxe Base allows high pigment loadings to achieve a soft yet high opacity print.

Multi-color printing can be achieved without the need for multiple flashing

Wash Resistance

CFX Deluxe Base, when correctly cured, will pass most specifier wash tests. For more stringent wash tests the use of a cross linker is recommended. No testing should be carried before a minimum of 24 hours after curing.

Compliance

All CFX Aqueous ink are formulated to be Phthalate Free, meet Oekotex standards and do not contain any Substances of Very High Concern. Currently, we, the manufacturer, do not test for compliance and should the user require certification we recommend they use an independent test house for verification.

Storage

Avoid direct sunlight and extremes of temperature.

Health and Safety

Please refer to the appropriate MSDS sheet

Application Recommendations

Fabric Types

Suitable for 100% Cotton

Mesh

From 34-90 threads per cm

Stencil

Water resistant Photo-Emulsion

Squeegee

Square Profile. 75/90/75 triple durometer

Additives

Water based inks can dry on the screen too quickly in low humidity situations. The addition of 2-5% of CFX Stellar Open Time Extender should resolve this issue.

To improve wash fastness and reduce tack we recommend adding 0.25 – 2% Stellar Crosslinker

Printing

Aquatint Pigments can be added at up to 12% by weight. We recommend leaving the image area flooded to prevent drying in the screen as well as the use of Open Time Extender and Water misting.

Flash Temperature / Gel Point

Maintaining a pallet temperature of 65°C / 150°F will maximize productivity on Multicolor designs. We recommend flash cures with hot air assistance for maximum efficiency.

Cure Temperature

160°C / 320°F for 120 - 150 seconds

Clean Up

For equipment use a Biodegradable Screen Wash. Clean up spills with a suitable absorbent material. Dispose of unused ink responsibly in accordance with local regulations

Disclaimer – Not all of our products are available in every Country – please check with our Sales Team for availability. The data presented in this bulletin is based on our current state of knowledge but does not absolve the user from carefully checking the product on receipt. We reserve the right to make changes on the basis of product improvement and raw material availability. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the products for a particular purpose.